

TECHNICAL DATA

POLYESTER FILM TAPE

Product Code: 1P801

P. Leo & Co (B. C.) Ltd.

150-12820 Clarke Place, Richmond, B.C. V6V 2H1, Canada

Telephone : (604)270-6115 * Facsimile : (604)538-2909 * E-mail : sales@pleo.com

Web Site : <http://www.pleo.com>



UL FILE #E126174

Description: 1P801 is a polyester film coated with a pressure sensitive Acrylic adhesive, Flame Retardant, Weather Resistance, high dielectric strength, excellent adhesive properties, outstanding heat and Solvent resistant, high tensile and dielectric strength.

Application: For the insulation and holding applications in transformers, capacitors, electric motors, relays stabilizers, and various kinds of electronic components. It is used as insulation material of class B.

Technical Details:

<u>PROPERTIES</u>	<u>UNITS</u>	<u>SPECIFICATION</u>
COLOR	-	*see below
TOTAL THICKNESS	mm	0.055±0.005
TENSILE STRENGTH	kg/25mm	9.5
ELONGATION	%	100
ADHESION TO STEEL	kg/25mm	0.8
DIELECTRIC BREAKDOWN	kV	DC 5.0 AC 3.0
TEMPERATURE CLASS	° C	130

* Color:

TR = transparent	RD = red	YE = yellow
BK = black	BL = blue	WH = white
GR = green	LY = lemon yellow	

Test Method: In accordance with ASTM method

Shelf Life: 6 months when storage at 73 ° and 65% relative humidity

Availability: Standard 66M roll, 3" core, width 960mm

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or the inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection therewith.

No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of Seller and manufacturer.